This presentation should not be considered a final statement of NIOSH policy or of any agency or individual who was involved. This information is intended for use in advancing knowledge needed to protect workers. Comments regarding this presentation may be submitted to the NIOSH Docket Office.

Chemical Warfare Agent (CWA) Simulant Project

Frank Palya
NIOSH/NPPTL Public Meeting
Hilton Garden Inn, Canonsburg, Pa









Purpose of CWA Simulant Project

takeholder wanted NIOSH to Identify nemical compounds that can simulate e permeation effects of GB and HD









Project Goals (Phase I)

- Identify chemical compounds that simulate the permeation effect of GB and HD through barrier materials
- Develop a laboratory procedure that can be used by stakeholders for estimating permeation breakthrough times using (GB and HD) simulants
- Provide Stakeholders with a low cost, rapid screening method for evaluating materials using available, low toxic simulants









Accomplishments (Phase I)

- 1.) Based on correlation, identified four (4) simulants that can be used to estimate CWA permeation through barrier materials:
- Nominal HD simulants
 - DCH 1,6-Dichlorohexane
 - CEPS 2-Chloroethyl phenyl sulfide
- Nominal GB simulants
 - DEMP Diethyl methylphosphonate
 - DIMP Diisopropyl methylphosphonate









Accomplishments (Phase I)

2.) Developed test procedure

- Used for testing liquid permeation resistance through nonporous barrier polymers
- Uses a new cell design, the Flooded Cell Technique, for testing both hard and soft barrier materials up to 1.0 cm thick
- Flooded Cell Technique: challenging chemical compound covers the entire surface area of the test specimen









Accomplishments (Phase I)

3.) Developed written test method

- Describes required equipment, procedures, and data analysis techniques; Also, includes mechanical drawings of permeation cell
- Test method will be published as an official **NIOSH** numbered document
- Status of document: peer review process initiated which will include (verification testing) of test method









Project Goals (Phase II)

- Improve estimation reliability of Flooded Cell Technique by testing additional simulants with other barrier materials
- Determine quantitative relationship between Flooded Cell Technique and conventional test loading (10 g/m²)
- Determine CWA/simulant sorption/desorption of representative barrier materials









Project Goals (Phase II) (cont)

- Identify critical properties of permeants and barrier materials that control permeation
- Develop capability to predict barrier permeation based on available chemical and physical properties of barrier polymers and permeating molecule









Project Status (Phase II)

Candidate materials selected

- Thermoplastics:
 - PVDF [Poly(vinylidine fluoride)] 0.05 mm
 - PP [Polypropylene] 0.04 mm
 - PET [Poly(ethylene terephthalate)] 0.006 mm
- Elastomers:
 - Poly(tetrafluoroethylene-co-propylene)
 AFLAS TM rubber 0.8–2.4mm









Project Status (Phase II) (cont)

Comparison tests

- Flooded cell vs. conventional (10 gm/m²) w/DIMP and DCH on butyl
- Breakthrough times essentially equal









Summary/Conclusion

- Developed a rapid, relatively low cost laboratory procedure that can be used to estimate CWA permeation through barrier materials
- Identified four (4) CWA simulants for permeation testing
- Developed written test method that describes equipment, test procedures, and data analysis techniques: peer review process initiated









Summary/Conclusion (cont)

Initiated Phase II of the CWA Simulant Project

Note: NIOSH or RDECOM does not guarantee that simulants identified will be suitable for all materials, nor does passage of manufacturer's pretest with a simulant guarantee passage of the official NIOSH certification testing










Liquid Permeation of EPDM with DIMP












Liquid Permeation Cell Component











Permeation Cell Photographs











